

# BURCOLEV K-PA



Burlington Chemical Company, Inc.  
Post Office Box 111  
Burlington, North Carolina USA 27216  
615 Huffman Mill Road  
Zip Code 27215

Leveling Agent for Premetallized Acid Dyes on  
Polyamide, Silk, and Wool

---

*Customer Technical Service*

*Providing Textile Innovations*

---

## ***What it does . . . Benefits and Features***

- Highly effective leveling for light-to-medium shades dyed with acid premetallized dyes on polyamide, wool, and silk
- Offers controlled rate-of-strike, exhaustion, and migration on hard-to-level dyes
- Promotes yarn barre coverage
- Compatible with anionic, cationic, and nonionic dyebath additives
- Specifically developed for light/pastel shades of 1:2 premetallized dyes on polyamide Type 6

---

## ***How it's used . . . Effective Application***

Suitable for all types of machinery.

Suggested use levels are 1.0 to 2.0% for acid premetallized with higher concentrations for lighter shades and lower concentrations for heavy shades.

Application is most ideal at a controlled, constant pH of 7.0 to 8.5.

---

## ***What it is . . . Physical Properties***

Appearance:	Yellow brown liquid
pH (10 g/L solution):	6.25
Ionic Nature:	Amphoteric
Specific Gravity:	1.09 g/cm <sup>3</sup>
Dilution:	Diluted with water at 27 – 38C (80–100F)

TB 14776  
11/6/05

---

**DISCLAIMER:** To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.