

**OGD  
Best Acid**

L, HL

	Polyamide	% Dyestuff (1/3 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/3 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/l activated chlorine)	
						(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
Yellow 2G 200%		0.28	100	100	5-6	2-3 4-5 4-5	4 5 5	4-5 4-5 4-5	4-5 5 5	4-5 4 4-5	4-5 4 4-5	4-5 4 4-5	4-5 4 5	1-2	1-2
Yellow NFG		0.2	100	20	5	3 3-4 4-5	4 4-5 5	4 3-4 4-5	4-5 4-5 5	4 3-4 4-5	3-4 4-5 5	4 3-4 4-5	4-5 4 5	2	3
Yellow GL		0.25	100	100	4-5	3 4-5 4-5	4-5 5 5	4-5 3-4 4	4-5 4-5 4-5	4-5 3-4 4	4-5 4-5 4-5	4-5 4 5	4-5 5 5	4-5	4-5
Yellow 4R		0.16	100	40	6	3 3-4 3	4-5 4 4	4-5 4-5 4-5	4-5 5 5	4-5 4 4	4-5 4-5 4-5	4-5 4-5 4-5	4-5 5 5	4-5	4-5
Yellow A4R 160% SP.		0.23	80	30	5	2 4-5 4-5	3-4 5 5	4-5 4-5 4-5	4-5 5 5	4 3-4 4-5	4-5 4 5	4 4 4-5	4-5 5 5	4	4-5
Yellow Brown 3GL		1.2	80	15	6	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	5 5 5	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	4	4-5
Red FRLL 200%		0.25	30	15	6	3 3 3-4	3-4 3-4 4	4-5 4 4-5	4-5 4-5 5	4 3-4 4	4-5 4 4-5	4 4 4-5	4-5 4-5 5	3-4	4-5
Pink BLRF		1.0	35	35	6	3 3-4 4-5	4 4-5 5	4-5 4 4-5	4-5 5 5	4-5 3 4	4-5 4 4-5	4-5 3-4 4-5	4-5 4-5 5	4	4
Red K-2BLL		0.26	80	40	5-6	3 3-4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 3-4 3-4	4-5 4 4	4-5 4 4	4-5 4-5 4-5	3	4-5
Red A2B 200%		0.26	40	20	5-6	3 2-3 3-4	3-4 3 4	4-5 4 4-5	4-5 4-5 5	4-5 3-4 4-5	4-5 4 5	4-5 4 4-5	4-5 4-5 5	3-4	4
Red A2B New		0.52	40	20	4	3-4 2-3 2-3	4 3 3	4-5 4-5 4-5	4-5 5 5	4 4 4	4-5 4-5 4-5	4 4 4-5	4-5 4-5 5	2	2-3
Red 3B New 250%		0.24	100	40	5-6	2-3 4 4-5	4 4-5 5	4 4 4-5	4-5 4-5 5	4 3 4-5	4-5 4 5	4 4 4-5	4-5 4-5 5	2-3	3-4
Floxine NK 200%		0.2	80	30	4-5	3 3 4-5	4-5 4 5	4 4-5 4-5	4-5 5 5	4 4 4-5	4-5 4-5 5	4-5 4-5 4	4-5 5 4-5	3	4
Sky Blue R		0.75	100	50	5-6	2 3 4	3-4 4 4-5	4-5 4 4-5	4-5 4-5 5	4 3-4 4	4-5 4 4-5	4-5 4 4-5	4-5 4-5 5	1-2	2
Blue AGL 250%		0.32	50	25	4-5	2 2-3 3-4	3-4 3 4	4-5 3-4 4-5	4-5 4 5	4 3 4-5	4-5 4 5	4-5 3-4 4	4-5 4 4-5	2	2-3

© bluesign® approved

Upper : Change of shade  
Medium : Staining on polyamide  
Lower : Staining on cotton