









**OGD
Best Acid**

L, HL

	Polyamide	% Dyestuff (1/3 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/3 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/1 activated chlorine)	
						(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)		(1/3 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
Blue 4RL		0.36	60	30	5	3-4 4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4 4-5	4 3-4 4-5	4-5 4 5	4-5 4 4-5	4-5 4 5	3	3-4
Blue NBRL 200% Special		0.33	60	30	5	2-3 3 3	3-4 3-4 4	4-5 4 4-5	4-5 4 4-5	4-5 3-4 4	4-5 4 4-5	4 4 4-5	4 4 5	2-3	3
Blue N2G		0.45	60	30	5-6	3 3 3-4	4 4 4	4-5 4 4-5	4-5 4 4-5	4 3-4 3-4	4-5 4 4	4-5 4 4-5	4-5 4 5	2-3	3

**OGD
Best Acid**

©

	Polyamide	% Dyestuff (1/1 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/1 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/1 activated chlorine)	
						(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
Yellow 8GX		2.0	100	90	2-3	2-3 4-5 3	4-5 5 4	4-5 2-3 4	4-5 4-5 4-5	3 2 2	3 3-4 3-4	3 2 3	3-4 4-5 4-5	1	1-2
Rhodamine B 400% New		2.4	40	30	2-3	2-3 4-5 4-5	3 5 5	4 1 1	4-5 4 4	1-2 1 1	2 3-4 3-4	2-3 1 1	3 4 4	1	1-2
Blue EA New		3.0	60	60	1	2-3 4-5 4-5	3 5 5	2-3 1 1	4 4-5 4-5	3-4 2 4	4 2 4	3 3 3	4 4-5 4-5	1	2-3
Blue 5GM		1.8	80	40	1	4 4-5 4-5	4-5 5 5	4-5 2-3 3	4-5 4-5 4-5	4-5 2-3 2	4-5 4 4	4-5 2-3 3	4-5 4-5 4-5	2-3	3
Green V 400%		0.9	80	60	1	2 4-5 4-5	2-3 5 5	4-5 2-3 2-3	4-5 4-5 4-5	3-4 2 3	4-5 4 4	4 3-4 4	4-5 4-5 4-5	3	4-5

© bluesign® approved

 Upper : Change of shade
 Medium : Staining on polyamide
 Lower : Staining on cotton