









OGD Best Acid	Polyamide	% Dyestuff (1/1 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/1 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/1 activated chlorine)	
						(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
Blue GLF 200%		1.4	60	40	4	3 2-3 4	4-5 3-4 4-5	4-5 3-4 4-5	5 4 5	4-5 2-3 4	4-5 3 4-5	4-5 3 4-5	5 4 5	3	4
© Blue AFN New		2.3	100	50	5	3 3 3-4	4 4 4-5	4-5 4 4-5	4-5 4 5	4 3 3-4	4-5 3 4-5	4-5 3-4 4-5	4-5 4 4-5	2	2-3
Blue AF-BL		2.3	80	40	5-6	3 3 4-5	4-5 4-5 5	4 4-5 4-5	4 5 5	4 4 4	4-5 4-5 4-5	4 4 5	4-5 5 5	1-2	2
Blue AF-GL		1.8	60	60	6	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	5 5 5	4-5 3 3	4-5 4-5 4-5	4-5 4 5	5 4-5 5	3-4	3-4
© Green GTSC 130%		1.6	60	30	6	3 4-5 4	4 5 4-5	4-5 2-3 4	4-5 4-5 5	4 2-3 3-4	4 4 4	4 2-3 4	4-5 4-5 4-5	4	4
Green N-GL 130%		1.5	60	30	6-7	4 4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 3 3	4-5 4-5 4-5	4-5 3-4 4	4-5 4-5 5	4	4
Dark Green A		0.6	60	30	5	3-4 4-5 3	4-5 5 4-5	4 3-4 4	4-5 4-5 5	4-5 3 3	4-5 4 4	4-5 3-4 4	4-5 4-5 5	1	2
Brown RS		1.0	60	40	4	4-5 4 3-4	4-5 4-5 4-5	4-5 4 4-5	4-5 4-5 5	4 4 3	4-5 4-5 4	4-5 4 4-5	4-5 4-5 4-5	2-3	3

© bluesign® approved

Upper : Change of shade
 Medium : Staining on polyamide
 Lower : Staining on cotton