










**OGD
Best Acid**

M

	Polyamide	% Dyestuff (1/1 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/1 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/l activated chlorine)	
						(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
© Blue BW H/C		1.9	80	50	5-6	3-4 4 4-5	4 4-5 5	4-5 4 4-5	5 4-5 5	4 4 4-5	4-5 4-5 4-5	4-5 4-5 4-5	4-5 4-5 5	2-3	2-3
Blue GSN		1.9	20	20	6	3-4 3 3	4-5 4 4	4-5 4 4-5	5 4-5 5	4 3-4 4	4-5 4 4-5	4-5 4 4-5	4-5 4-5 5	2-3	2-3
Blue NGL 180% SPECIAL		1.3	30	15	5	4-5 3 4	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4-5 4-5	4-5 4 4-5	4-5 4-5 5	2	2-3
© Turq. Blue 3G		3.5	100	50	2	1 4 3-4	1 4-5 4	2 3-4 3	2-3 4-5 4	1 3 2	1 4 4	2-3 3-4 2	2-3 4-5 4	1	2-3
© Green 6GW		2.0	40	30	6-7	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	4-5 4 4-5	4-5 4-5 5	4-5 4-5 4-5	4-5 5 5	2-3	3
Green 5GW 180%		1.4	30	15	6	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	5 5 5	4-5 4 4-5	4-5 4-5 4-5	4-5 4-5 4-5	4-5 5 5	2-3	2-3
© Green GW 130%		1.6	30	10	6	4 4-5 4-5	4-5 5 5	5 3 4	4-5 4-5 4-5	4 3 3-4	4 4-5 4-5	4-5 4 4	4-5 4-5 5	3	4
© Cyanine 5R H/C		* 1.1	80	60	6	4-5 3 3-4	4-5 4-5 4-5	4-5 4 4-5	4-5 4-5 5	3-4 4 4-5	4-5 4-5 5	4 4-5 4	4-5 5 5	2	3
Black NBRS 200%		* 1.8	40	40	4-5	4-5 4-5 4	4-5 5 4-5	4-5 4-5 4-5	5 5 5	4-5 4 4	4-5 4-5 4-5	4-5 4-5 4-5	5 5 5	4-5	4-5

© bluesign® approved

* : 2/1 S.D.

Upper : Change of shade
Medium : Staining on polyamide
Lower : Staining on cotton