








OGD Best Acid SUPRA SF	Polyamide	% Dyestuff (1/1 S.D.)	Solubility (80°C) in g/l	Stability of solution (80/25°C) in g/l	Light fastness ISO 105-B02 (1/1 S.D.)	Fastness to washing 50°C ISO 105-C02		Fastness to water ISO 105-E01		Fastness to perspiration ISO 105-E04 (alkaline)		Fastness to perspiration ISO 105-E04 (acid)		Fastness to chlorinated water ISO 105-E03 (50mg/1 activated chlorine)	
						(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)		(1/1 S.D.)	
						without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment	without aftertreatment	aftertreatment
⊙ Royal Blue DR New		2.3	40	25	5	4-5 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	1-2	2
⊙ Blue SF-ML		3.0	30	30	5-6	4-5 4 4-5	5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 3-4 4	4-5 4-5 4-5	4-5 4 4-5	4-5 5 5	1-2	2
⊙ Br. Blue SF-GW		3.5	80	60	5	3 4-5 4-5	4 5 5	4 2 3-4	4-5 4 4-5	4 2 2-3	4-5 4-5 4	4 3 3-4	4-5 4 4-5	1	2
Sky Blue SF-BWF		2.7	40	20	6	4 4 4-5	4-5 4-5 5	4-5 2 3	4-5 4 4	4-5 2 2	4-5 4 4	4-5 3 3	4-5 4-5 4-5	2	3
Blue SF-BG		1.3	30	15	5	4-5 3 4	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	4-5 4 4-5	4-5 4-5 5	2	2-3
⊙ Green SF-GW 130%		1.6	30	10	6	4 4-5 4-5	4-5 5 5	5 3 4	4-5 4-5 4-5	4 3 3-4	4 4-5 4-5	4-5 4 4	4-5 4-5 5	3	4
⊙ Br. Green SF-6G		2.0	40	30	6-7	4 4-5 4-5	4-5 5 5	4-5 4-5 4-5	4-5 5 5	4-5 4 4-5	4-5 4-5 5	4-5 4-5 4-5	4-5 5 5	2-3	3

⊙ bluesign® approved

Upper : Change of shade
Medium : Staining on polyamide
Lower : Staining on cotton

The information given is correct to the best of our general knowledge without guarantee or warranty. It is the responsibility of the user to test the suitability of the products under their processing conditions.