

BURCO® ACID VS-1



Burlington Chemical Company, Inc.
Post Office Box 111
Burlington, North Carolina USA 27216
615 Huffman Mill Road
Zip Code 27215

耐隆酸性染料染色 pH 控制劑

Customer Technical Service

Providing Textile Innovations

What it does . . . 效益與特性

- 控制染浴 pH 值降到 4.0-4.5 之酸性環境，不需再添加酸。
- 促進酸性染料於耐隆染色之均染性。
- 去除加酸以吸盡酸性染料之步驟，縮短染程。
- 較傳統於染程中加硫酸氨和/或酸之系統更易控制。

How it's used . . . 實務應用

適用於噴射、絞紗、筒子紗、散毛和經軸染色機。

批次式染色，建議用量為 1 g/l 到 2.5 g/l，染浴起始 pH 以純鹼。

使用濃度可能因水、助劑、染料之 pH 值影響而有所不同。

What it is . . . 物性資料

外觀：	清澈液體
pH (10 g/L 溶液)：	4.0
離子性：	陰離子
比重：	1.15 g/ cm ³
稀釋：	使用時以 27-38°C (80-100°F) 的水稀釋

TB 14563
10/16/06

DISCLAIMER: To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.