

BURCO® BUFFER BFG

耐隆合金與混合染料染色 pH 控制劑



Burlington Chemical Company, Inc.
Post Office Box 111
Burlington, North Carolina USA 27216
615 Huffman Mill Road
Zip Code 27215

Customer Technical Service

Providing Textile Innovations

What it does . . . 效益與特性

- 耐隆以合金酸性染料及混合染料染色時，提供穩定、可控制的 pH 值。
- 有助於促進均染並避免因 pH 變化而改變染色上色速率。
- 淺、中色系較難之顏色，可與 Burcolev K-PA 並用以促進均染並改善橫條覆蓋性。
- 染程中可控制 pH 值。

How it's used . . . 實務應用

適用於噴射、絞紗、筒子紗、散毛和經軸染色機。

批次式染色，建議用量為 0.75 g/l 到 1.5 g/l，染浴 pH 控制在 6.0-7.0。

使用濃度可能因水、助劑、染料之 pH 值影響而有所不同。

What it is . . . 物性資料

外觀：	清澈液體
pH (10 g/L 溶液)：	6.0
離子性：	-- (不適用)
比重：	1.28 g/ cm ³
稀釋：	易稀釋於 27 – 38°C (80–100°F) 的水中

TB 14805
11/9/05

DISCLAIMER: To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.