

## 用於吸濕快乾加工的吸濕加工劑

Burlington Chemical Company, Inc.  
Post Office Box 111  
Burlington, North Carolina USA 27216  
615 Huffman Mill Road  
Zip Code 27215

*Customer Technical Service*

*Providing Textile Innovations*

### *What it does . . .* 效益與特性

- 對合纖包括尼龍、聚酯、壓克力、aramids 及其混合纖維素纖維、羊毛、蠶絲等賦予濕氣移轉特性(芯吸性)
- 優越的耐洗性
- 提供好濕潤性及抗靜電性
- 改善手感及垂感

### *How it's used . . .* 實務應用

適合合纖布用浸染法及軋壓法

浸染法用 1.0 ~ 4.0 % 於染色後出缸前 49-71C (120-160F) ×15-30 分, 或用於螢光劑染色浴中。

連續式軋壓法用 10.0 ~ 40.0 g/L 於 27-32C (80-90F) 軋壓, 烘乾/焙乾用一般的後定條件。

### *What it is . . .* 物性資料

外觀：                  白色乳液  
pH (10 g/L 溶液)：8.6  
離子性：              非離子  
比重：                  1.03 g/cm<sup>3</sup>  
稀釋：                  易稀釋於 27 - 38°C (80-100°F) 的水中

**TB 10100**  
**11/2/05**

**DISCLAIMER:** To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.