

BURCO® LUBRICANT JPL



前處理及染色浴中柔軟劑

Burlington Chemical Company, Inc.
Post Office Box 111
Burlington, North Carolina USA 27216
615 Huffman Mill Road
Zip Code 27215

Customer Technical Service

Providing Textile Innovations

What it does . . . 效益與特性

- 避免織物加工時之裂紗、折痕與繩狀斑。
- 結合聚酯與聚醚之化學性質，使纖維與纖維、纖維與金屬及纖維與水之間具有獨特之平滑性。
- 促進手感與車逢性。
- 筒子紗染色時有助於水流循環，降低因內外層差產生之不均染現象。
- 良好之 PH 與電解質安全性。

How it's used . . . 實務應用

適合各類紗線之筒子紗、絞紗之加工或針織、梭織物之加工。

建議用量：1.00 – 2.00 g/L.

What it is . . . 物性資料

外觀：	淺色液體
pH (10 g/L 溶液)：	7.0
離子性：	非離子/陰離子
比重：	1.00 g/ cm ³
稀釋：	以 27 – 38°C (80–100°F)的水稀釋

TB 14060
11/6/05

DISCLAIMER: To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.