

BURCO® SCOUR LFE-810



Burlington Chemical Company, Inc.
Post Office Box 111
Burlington, North Carolina USA 27216
615 Huffman Mill Road
Zip Code 27215

精練及乳化劑

Customer Technical Service

Providing Textile Innovations

What it does . . . 效益與特性

- 對於合成纖維與天然纖維具有高性能的精練及乳化性。
- 優越的濕潤性與清洗力、以及對礦物油與矽酮油之乳化性能。
- 對彈性織物有效乳化礦物油與矽酮油。
- 應用於染浴及固色浴以繼續乳化足以產生白斑的殘留油劑。
- 低泡性，適合所有各種製程及設備。

How it's used . . . 實務應用

使用在批次前處理時，推薦用量 0.25 ~ 1.00 g/L 49 – 82°C (120-180°F).

使用於染色浴及固色浴時，推薦用量 0.15 ~ 0.25 g/L.

針織物及梭織物的連續前處理，推薦用量 5.0 ~ 10.0 g/L.

請參考 TD3030-12 應用推薦.

What it is . . . 物性資料

外觀：	清澈液體
pH (10 g/L 溶液)：	5.0
離子性：	非離子
比重：	0.96 g/mL
稀釋：	易稀釋於 27 – 38°C (80–100°F)的水中

TB 10499
10/2/06

DISCLAIMER: To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.