

BURCOTEX NSU



耐隆/彈性纖維之染色促進劑

Burlington Chemical Company, Inc.
Post Office Box 111
Burlington, North Carolina USA 27216
615 Huffman Mill Road
Zip Code 27215

Customer Technical Service

Providing Textile Innovations

What it does . . . 效益與特性

- 耐隆/彈性纖維染色時，促進酸性/酸性含金染料對彈性纖維之上色率，改善彈性纖維浮白的現象。
- 促進染料之均染與移染，不需再加均染劑。
- 適合各類型染機。

How it's used . . . 實務應用

建議用量 0.5 – 2.0%，依顏色深淺、染料選擇與彈性纖維含量而定，不需額外添加均染劑或緩染劑。

注意：提升彈性纖維之上色率可能導致濕牢度降低，即使經後處理(固色)亦同。

What it is . . . 物性資料

外觀： 清澈淺黃色液體
pH (10 g/L 溶液)：5.5
離子性： 陽離子
比重： 1.0 g/ cm³
稀釋： 以 27 – 38°C (80–100°F)的水稀釋

TB 10619
11/2/05

DISCLAIMER: To our best knowledge, the information and recommendations contained herein are accurate and reliable. However, this information and our recommendations are furnished without warranty, representation, inducement, or license of any kind, including, **but not limited to the implied warranties of merchantability and fitness** for a particular use or purpose. Customers are encouraged to conduct their own tests and to read the product labels carefully before using them. Furthermore, the customer assumes sole liability for any patent infringement that occurs by reason of its following our recommendations or using the information given.